

Amendments to the Claims

A detailed list of all claims under examination is set out below. Please cancel claims 18-21 without prejudice. A complete set of the thus-pending claims is shown below:

1. (original): A process for making single-phase lithium-transition metal oxide compounds containing cobalt, manganese and nickel comprising:
 - a) wet milling cobalt-, manganese-, nickel- and lithium-containing oxides or oxide precursors to form a finely-divided slurry containing well-distributed cobalt, manganese, nickel and lithium, and
 - b) heating the slurry to provide a lithium-transition metal oxide compound containing cobalt, manganese and nickel and having a substantially single-phase O3 crystal structure.
2. (original): A process according to claim 1 wherein water is used for wet milling.
3. (original): A process according to claim 1 comprising milling the slurry until it contains particles having an average particle diameter less than about 0.3 μm .
4. (original): A process according to claim 1 comprising milling the slurry until it contains particles having an average particle diameter less than about 0.1 μm .
5. (original): A process according to claim 1 comprising milling the powders using ceramic media.
6. (original): A process according to claim 1 wherein the precursors comprise one or more carbonates.
7. (original): A process according to claim 6 wherein at least one of the precursors comprises manganese or nickel carbonate.
8. (original): A process according to claim 1 comprising milling together equimolar amounts of manganese- and nickel-containing oxides or oxide precursors.

9. (original): A process according to claim 1 comprising heating the slurry at a rate of at least $10^{\circ}\text{C}/\text{min}$ to a temperature of at least 800°C .
10. (original): A process according to claim 1 comprising heating the slurry to a temperature at or below 1050°C .
11. (original): A process according to claim 1 wherein the lithium-transition metal oxide compound is selected from those represented by the formula $\text{Li}_a[\text{Co}_x(\text{Ni}_{1/2}\text{Mn}_{1/2})_{1-x}]\text{O}_2$, where $0 \leq a \leq 1.2$ and $0.1 \leq x \leq 0.98$.
12. (original): A process according to claim 1 wherein the lithium-transition metal oxide compound has the approximate formula $\text{Li}(\text{Co}_{0.8}\text{Mn}_{0.1}\text{Ni}_{0.1})\text{O}_2$.
13. (original): A process according to claim 1 wherein the lithium-transition metal oxide compound has the approximate formula $\text{Li}(\text{Co}_{1/3}\text{Mn}_{1/3}\text{Ni}_{1/3})\text{O}_2$.
14. (original): A process according to claim 1 wherein the lithium-transition metal oxide compound has the approximate formula $\text{Li}(\text{Li}_{0.08}\text{Co}_{0.15}\text{Mn}_{0.375}\text{Ni}_{0.375})\text{O}_2$.
15. (original): A process according to claim 1 further comprising mixing particles of the lithium-transition metal oxide compound with conductive carbon and a binder and coating the resulting mixture onto a supporting substrate to form a lithium-transition metal oxide cathode.
16. (original): A process according to claim 15 further comprising placing the cathode, an electrically compatible anode, a separator and an electrolyte into a container to form a lithium ion battery.
17. (original): A process according to claim 16 wherein the battery capacity does not substantially decrease after the battery is charged and discharged between 4.4 and 2.5 volts for at least 100 cycles at a 75 mA/g discharge rate.

Claims 18-21 cancelled.